



VpCI® ADDITIVES FOR COATINGS, FLUIDS, ADHESIVES AND PLASTICS

M-380

PRODUCT DESCRIPTION

M-380 is a water-based corrosion inhibitor that is designed to be used with carboxylated acrylic or styrene-acrylic latices. M-380 provides corrosion inhibition to ferrous and non-ferrous surfaces.

M-380 should be mixed before use although no settling is anticipated. The recommended starting levels for M-380 should be 1% to 3% based on the total weight of the formulation.

FEATURES

- Excellent corrosion resistance
- Synergistic effect with Cortec® M-119 at 1%
- Can be post-added to batch
- Low viscosity
- No VOCs
- Does not lower gloss
- Improves salt spray, humidity performance and cohesion
- Synergistic effects with M-119/M-119LV
- Non-toxic formulation

LIMITATIONS

The latex should be always tested for compatibility with M-380 by slowly adding M-380 to a complete formulation with mixing.

PHYSICAL PROPERTIES

Appearance	Hazy to opaque off-white slightly viscous liquid
Odor	Strong ammonia
pH	10-12 (Neat)
Density	9.9-10.2 lb/gal (1.19-1.22 kg/l)
Weight Solids	15.7%
Volume Solids	5.4%
VOC	0

PACKAGING AND STORAGE

M-380 is available in 5 gallon (19 liter) plastic pails, 55 gallon (208 liter) metal drums, liquid totes and bulk. M-380 should be stored in heated warehouse conditions to avoid freezing. Shelf life is 6 months or longer.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
 Phone (651) 429-1100, Fax (651) 429-1122
 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
 Internet <http://www.CortecVpCI.com>

printed on recycled paper 10% post consumer

Revised 7/11/2003. Cortec Corporation 2003. All rights reserved. Supersedes: 7/11/00. Cortec® is a trademark of Cortec Corporation.

Distributed by:



OTiK Sp. z o.o.

ul. Hutnicza 4
 81-061 Gdynia
 tel.: 58 6230498
 fax: 58 6230496

otik@use.pl

www.inhibitory.use.pl



Certificate No.70781

Certificate No.81867