


# VpCI™ ADDITIVES FOR COATINGS, FLUIDS, ADHESIVES AND PLASTICS



## M-109



### PRODUCT DESCRIPTION

M-109 is a multimetal solvent-based organic vapor and contact corrosion inhibitor for use in solvent and some waterborne coatings. The use level recommended is 1 to 3% by weight.

### FEATURES

- Excellent multimetal corrosion protection
- Does not contain hazardous zinc phosphate, chromates, or barium-based inhibitors
- Low toxicity
- Excellent thermal stability [up to 320°F (160°C)]
- Can be post added to most coating system
- VOC free
- Compatible with solvents based and some waterborne coatings

### FORMULATION NOTES

M-109 can be post added to most coatings. It must be added to the amine part in a two part epoxy. M-109 should be added to a waterborne alkyd before neutralization with amines. Starting point levels of 1 to 3% are recommended.

### PHYSICAL PROPERTIES

Appearance	Dark amber viscous liquid
Viscosity	3000 to 6000 cps at 6 rpm
Density	8.0-8.3 lb/gal (0.96-1.00 kg/l)
Non-volatile (weight)	95-100%
Flash Point	>320°F (160°C)

### METALS PROTECTED

- Carbon steel
- Stainless steel
- Galvanized steel
- Cold rolled steel
- Aluminum
- Brass
- Copper
- Solder
- Bronze

### SUGGESTED USES

- Solvent-based coatings
- Some waterborne alkyds, latices, and epoxies

### PACKAGING

M-109 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes and bulk.

**FOR INDUSTRIAL USE ONLY**  
**KEEP OUT OF REACH OF CHILDREN**  
**KEEP CONTAINER TIGHTLY CLOSED**  
**NOT FOR INTERNAL CONSUMPTION**  
**CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION**

#### **LIMITED WARRANTY**

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

**BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.** No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

**THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC, E-mail [info@cortecvci.com](mailto:info@cortecvci.com)  
Internet <http://www.cortecvci.com>

printed on recycled paper  10% post consumer

Revised 6/21/06 Cortec Corporation 2004-2006. All rights reserved. Supersedes: 12/2/04  
© 2004-2006, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited